Technical specificationsMarmoleum meets the requirements of EN-ISO 24011
Marmoleum Acoustic meets the requirements of EN 687 Marmoleum Decibel meets the requirements of EN 686 $\,$









			Marmoleum 2.0 mm Real/Fresco	Marmoleum 2.5 mm Real/Fresco/Vivace/ Splash/Terra	Marmoleum 3.2 mm Real/Fresco	Marmoleum Decibel	Marmoleum Acoustic
	Total thickness	EN-ISO 24346	2.0 mm	2.5 mm	3.2 mm	3.5 mm	4.0 mm
	Surface finish		Topshield pro	Topshield pro	Topshield pro	Topshield pro	Topshield pro
	Domestic use	EN-ISO 10874	Class 23	Class 23	Class 23	Class 23	Class 23
	Commercial use	EN-ISO 10874	Class 32	Class 34	Class 34	Class 33	Class 33
	Light Industrial use	EN-ISO 10874	Class 41	Class 43	Class 43	Class 41	Class 41
	Collection size		29	90	8	14	6
	Roll width	EN-ISO 24341	2.0 m	2.0 m	2.0 m	1.95 / 2.0 m	2.0 m
\Box	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m
	Total weight	EN-ISO 23997	2300 g/m²	2900 g/m²	3900 g/m²	3100 g/m ²	4000 g/m²
	Residual indentation Typical value	EN-ISO 24343-1	≤ 0.15 mm ~0.07 mm	≤ 0.15 mm ~0.08 mm	≤ 0.15 mm ~0.10 mm	≤ 0.30 mm ~0.20 mm	≤ 0.40 mm ~0.25 mm
6	Castor chair continuous use	ISO 4918	Pass	Pass	Pass	Pass	Pass
7	Color fastness to light	EN-ISO 105-B02 method 3	≥ 6	≥ 6	≥ 6	≥ 6	≥6
3	Flexibility	EN-ISO 24344	ø 30 mm	ø 40 mm	ø 50 mm	ø 40 mm	ø 60 mm
₹	Resistance to chemicals	EN-ISO 26987	Resistant to dilu	ted acids, oils, fats and to th	e conventional solvents. Not	resistant to prolonged ex	posure to alkalis.
e *	Bacteriostatic properties*		Marmoleum has natural b	pacteriostatic properties which are confirmed by independent laboratories, even against the bacteria MR			
	Cigarette resistance EN 1399 There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result of stubbed-out cigarettes can						rettes can be removed
**************************************	Slip resistance (ramp test)	DIN 51130	R9	R9	R9	R9	R9
	Acoustical impact noise reduction	EN-ISO 717-2	-	-	-	18 dB	14 dB
	Indoor Air Emissions: TVOC at 28 days	EN 16516	≤ 0.01 mg/m³	≤ 0.01 mg/m³	≤ 0.01 mg/m³	≤ 0.01 mg/m³	≤ 0.01 m g/m³
<u> 72</u>	Marmoleum Ohmex 2.5 mm is available in different colour	rs:	Electrical resistance 1 x $10^{\circ}\Omega$ < R1 < 1 x $10^{\circ}\Omega$ (static dissipative) tested in accordance with EN 1081 Marmoleum is climate positive cradle to gate**.				
∞	Creating better environmen	nts					
LCA	Life Cycle Assessment		LCA is the foundation for securing the lowest environmental impact.				
イ	renewable electricity		Marmoleum is manufactured using 100% electricity from renewable sources.				
•				Marmolous	idf 04 000/tl	materials.	
				Marmoleur	m is made of 94-98% natural		
	natural materials (e.				m is made of 94-98% natural m contains PEFC certified we	ood flour.	
	natural materials (e. tree resin, wood flou			Marmoleu			
e e	tree resin, wood flou			Marmoleu Marmoleum is free	m contains PEFC certified we	er and plasticizers.	
	tree resin, wood flou	ur, limestone)	yes	Marmoleu Marmoleum is free	of PVC, PET, synthetic rubbe	er and plasticizers.	yes
	recycled content	ar, limestone)	<u> </u>	Marmoleu Marmoleum is free Marm	on contains PEFC certified we of PVC, PET, synthetic rubbe oleum contains recycled con	er and plasticizers.	yes
	recycled content Application on underfloor he	ar, limestone)	<u> </u>	Marmoleu Marmoleum is free Marm	on contains PEFC certified we of PVC, PET, synthetic rubbe oleum contains recycled con	er and plasticizers.	
	recycled content Application on underfloor he	ur, limestone) ating uirements of EN 14	041:2004	Marmoleu Marmoleum is free Marm yes	on contains PEFC certified we of PVC, PET, synthetic rubbe oleum contains recycled con yes	er and plasticizers. Itent. yes	
(E	recycled content Application on underfloor he Marmoleum meets the req Product code	ar, limestone) ating uirements of EN 14	041:2004 0100201-DoP-107	Marmoleum is free Marm yes 0100201-DoP-107	on contains PEFC certified we of PVC, PET, synthetic rubbe oleum contains recycled con yes	er and plasticizers. tent. yes 0100207-DoP-107	0100206-DoP-107

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.



Thermal conductivity



0.17 W/mK

^{*} Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions.

** For details, please consult the EPD for Marmoleum 4790690881.101.1

*** Marmoleum 2.5 mm is available in reaction to fire classification B_n's1, G, CS. Available on request, contact sales support for leadtime.