

**RUST-OLEUM®**

INDUSTRIAL



## COMBICOLOR® ORIGINAL AEROSOLS

# One coat system for metal protection, direct to rust

- Primer and topcoat in one
- For application onto rust, bare metal
- Usable down to 5°C

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# COMBICOLOR® ORIGINAL AEROSOLS

## BESKRIVNING

RUST-OLEUM® CombiColor Aerosols High Gloss 7300 are based on a urethane modified alkyd. Lead- and chromate-free - contains rust-inhibitive pigments for additional corrosion protection - good hiding properties - high gloss appearance.

## REKOMMENDERAD ANVÄNDNING

RUST-OLEUM CombiColor Aerosols High Gloss 7300 can be applied directly on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols High Gloss 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols High Gloss 7300 should be used in light industrial exposures, normal humidity and interior applications.

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Hanteringstorr: 6 hours  
Torktid: After 2 hours  
Fullt härdad: 7 days

## ÅTGÅNG

2 - 3 m<sup>2</sup> per spray can (400 ml).

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiPrimer Tack Coat 3302.

## APPLICERINGSFÖRHÅLLANDEN

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

## APPLICERING OCH SPÄDNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## INFORMATION

Prevent application of too thick layers because this can cause problems with drying and sagging. CombiColor Aerosols can be applied on 7300 Metal (brush version) within 4 hours or after 72 hours.

## SÄKERHETSDATA

VOC-nivå: 535 - 540 g/l  
Anmärkningar om säkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)